

## T-POL 3600

TWO COMPONENT, SOLVENT BASED, GLOSSY FINISH, UV RESISTANT, ALIPHATIC POLYURETHANE TOPCOAT

### Description of Product

T-POL 3600, is a two component solvent base, low viscosity, self leveling, aliphatic polyurethane based, UV resistant, and painting and top coating featuring glossy surface appearance.

### Fields of Application

- On concrete and cement based mineral surfaces
- Interior and exterior spaces
- To obtain gloss finish coat, in smooth or sand broadcast surface applications
- A high level of hygiene required fields such as hospitals, laboratories and clean rooms
- Kindergartens and in nursing homes
- For outdoor and indoor swimming pools

### Advantages

- High bond strength on moist surfaces
- Low viscosity
- Because of low VOC content, it is an environmentally friendly product
- It has excellent penetration properties
- It has a hard elastic structure
- Easy application, maintenance and cleaning
- High UV resistance
- Glossy appearance
- Hygienic and anti bacterial
- Resistant to mechanical loads, abrasion and chemicals

### Appearance

Mix (Part A +Part B): Ral colors

### Packaging

Part A: 15 kg. net – Part B: 5 kg. net

Total: Part A+B: 20 kg. net – Part A+B: 22.55 kg. gross

### Storage

Store in original sealed containers in a cool dry environment at temperatures between +5°C and +30°C.

### Shelf Life

Minimum 12 months for part A and 9 months for part B from date of production if stored in original unopened containers. Once opened, product should be consumed within one week as it is stored under appropriate storage conditions.

### Chemical Structure

Part A: Polyurethane Resin Part B: Polyurethane Hardener

### Technical Specifications

All technical values were calculated based on +23°C and 50% relative humidity. Temperature and humidity changes would change technical values.

### T-POL 3600 Technical Data

Density	Mixed Resin: 1,20-1,30 kg/liter
Shore D Hardness	7 days: 70 – 80 (ASTM D2240-05)
Abrasion Strength	7 days : <50mg (± %3) (CS 10/1000/1000) (ASTM D4060 – 14)
Duration of Use After Mixing	3-4 hour
Consumption	0,300 kg/m <sup>2</sup> for two layer(0,150kg+0,150kg) *between coat time min10h, max 48h
Powder Dryness	2-3 hour / 23°C
Touch Dryness	3-4 hour / 23°C
Total Curing Time	7 days
Application Format	Roll,Bruch

### Preparation of Substrate

Concrete substrates must be sound and of sufficient compressive strength (minimum 25 N/mm<sup>2</sup>) with a minimum pull off strength of 2,5 N/mm<sup>2</sup>. The residual moisture content of the substrate must not exceed 4%, the substrate temperature should remain a minimum of +8°C and the temperature of the substrate must be at least +3°C above the current dew point temperature.

The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. Oil-contaminated substrates must first be pre-cleaned with an emulsifying cleaning detergent in accordance with the supplier's instructions. Finally, the concrete or cement screed surface is cleaned using high-pressure water jetting. Excess water is removed from the surface by wet and dry vacuum cleaner.

Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve a profiled open textured surface. The surface should be vacuumed by industrial vacuum cleaners to remove dust.

If in doubt of the surface, apply a test area first. Should not be applied to wet or frozen surfaces and surfaces with high humidity.

Before applying t-pol 3600, the substrates should be primed with appropriate Momentum prime (according to the ground) materials.

### Application Conditions

During the application, ambient temperature should be between +10°C and +30°C. Relative Air Humidity should not exceed 80% and the substrate temperature should be between +10°C and +30°C. Substrate humidity should be maximum 4%. Substrate temperature shouldn't be less than +8°C and must be at least +3 °C above the current dew point temperature.

Before applying T-pol 3600, the substrates should be primed with appropriate Momentum prime (according to the ground) materials.

### Mixing

Make sure that the product temperatures are between +10°C and +30°C before starting the mixing procedure. Prior to mixing, stir part A and B separately with a mechanical drill and paddle at a very low speed. Add component B gradually into component A and mix till you reach a homogeneous consistency (Approximately 3 minutes).

Pour the contents into a clean container and mix for another couple minutes. Please avoid mixing on high speed and do not add any solvent, etc. into the mixture during the application procedure.

### Application Procedure

Avoid application under excessive heat or wind, rain and/or when the ambient and/or substrate temperature is below +10°C or above +30°C. In extremely cold conditions, heaters should be used to increase the ambient and the workability of the product.

After the mixing procedure, T-POL3600 can be applied to a surface, which is already primed with appropriated momentum primer, with roller brush. Make sure that a continuous, pore free coat covers the substrate.

For exact color matching, ensure the T-POL 3600 in each area is applied from the same control batch numbers.

If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO<sub>2</sub> and H<sub>2</sub>O water vapor, which may adversely affect the finish. For heating use only electric powered warm air blower

system.

Mixed product should be applied in max. 30 minutes in about +20°C. Waiting time between the coats is min 10, max 48 hours. The surface should be sanded if waited more than 48 hours between coats. The product would be completely cured in minimum 7 days to reach its maximum mechanical and chemical resistance.

Reaction times of resin based systems depend on ambient and substrate temperatures as well as relative humidity. Under lower temperatures reaction times are longer which increases pot life, coating interval and working time. High temperatures increase chemical reactions and the above mentioned time decreases accordingly.

After application, the material should be protected from direct contact with water for a minimum of 48 hours. Within this period, contact with water can cause a surface carbonation and/or surface tackiness, both of which must be removed. In such cases, overall coating should be removed from the floor and renewed.

To maintain the appearance of the floor after application, T-POL 3600 must have all spillages removed immediately and must be regularly cleaned using rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques etc. using suitable detergents and waxes.

Epoxy and polyurethane flooring systems, should be performed by expert contractors.

### Cleaning of Tools

Clean all tools and application equipment with thinner immediately after use. Hardened/cured material can only be mechanically removed.

### Health and Safety Information

The following protective measures should be taken when working with the material: Wear safety gloves, goggles and protective clothing. Because of irritation, effects of the uncured material, components should not come in contact with the skin or eyes. In cases of contact, the affected area should be washed with plenty of water and soap. If swallowed, seek medical attention immediately. Do not drink or eat at the application site. Keep out of reach of children.

### Product Liability

Momentum is just responsible for the quality of the Momentum labelled products. All the data referred herein are gathered as a result of practical and scientific studies. Momentum cannot be legally obligated or responsible for any damage unless correct product is used accurately in suitable areas and under right conditions.

### Legal Notes

All the information and references herein regarding Momentum labelled products are provided in good faith in accordance with Momentum's knowledge and experience. Application fields and surfaces of the products may alter in different situations. It must be ensured that the correct product is used accurately in suitable areas and under right conditions. All the commercial factors, data and instructions regarding applicability provided by Momentum should be abided through implementation.

Momentum cannot be legally obligated or responsible for any damage that may occur due to failure to abide by the instructions provided by Momentum. The third party applicators/users should run all the necessary tests for the accurate usage of the products. Momentum reserves all the rights for alteration of the products. The applicators/users should observe intellectual property rights of the third parties. When the order is confirmed, all technical requirements are essential in respect of existing sales and transportation.

